

URETHANE

COATINGS

POLYURETHANE SPECIALISTS SINCE 1979

TECHNICAL DATA SHEET

MODIFIED OIL MATT is a transparent, single pack, organic oil based timber finish (modified with polyurethane providing significantly improved wear resistance) that will preserve and enhance interior timber, parquetry and particle board flooring.

Uses: MODIFIED OIL MATT is ideal for coating New Timber Floors suspected of being prone to shrinkage. MODIFIED OIL MATT will greatly reduce the occurrence of edge bonding. MODIFIED OIL MATT is ideal for clients concerned about exposure to fumes from Polyurethane as it is less likely to cause discomfort because only white spirit is used as the solvent. MODIFIED OIL MATT is not as subject to sheen variation as Low sheen Polyurethanes. MODIFIED OIL MATT is completely compatible with Urethane Coatings MODIFIED OIL GLOSS, MODIFIED OIL SATIN and TUNGSEAL.

Physical Description & Product Specification

		MODIFIED OIL SATIN
Appearance		Slightly opaque liquid, mild solvent odour.
Colour		Wet - Dark purple/amber. Dry - Mild amber.
Drying Time (hours) @ 25°C and 50% R.H.		Reduced temperature and/or increased humidity will slow drying (extend each drying phase).
	Dust Free	1.00
	Tack Free	2.00
	Print Free	4.00
	Hard Dry	6.00
Reflectance	(%)	20-30%
Viscosity @ 25°C (seconds)		19-23
Solid Content	(%)	36 (±1)%
Wet film per coat	(mm)	0.100
Dry film per coat	(mm)	0.036
Solubility		Not Soluble in Water.
Specific gravity (H₂O = 1):		0.879
Sanding & Recoat @ 25°C and 50% R.H. (Hours)		5.5 – 6.0
Sanding properties		Excellent
Thinning	(Not Recommended)	Add 5-10% MINERAL TURPENTINE if a higher coverage and a thinner coat is required.
Coverage	(m ² /Litre)	10.
Full Cure	(Days)	7.
Shelf life	(Months)	12.

Product Slip Resistance – AS/NZS 4586:2004

MODIFIED OIL has been evaluated by ATTAR (Advanced Technology Testing and Research) against Test Standard; AS/NZS 4586; 2004 Slip Resistance Classification of New Pedestrian Surface Materials; [Dry Test Standard – Appendix B]

DRY SLIP RESISTANCE – refer Appendix 1 – TABLE 3, CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS ACCORDING TO THE DRY FLOOR FRICTION TEST.

Classification is F [≥ 0.4]. (Actual test result: Dynamic Coefficient of Friction - Mean of 0.75).

Application Data**Floor Preparation:****General:**

1. Check that timber is adequately seasoned as if not, any subsequent cracking warping and shrinkage may compromise adhesion.
2. Ensure the surface is dry and thoroughly clean, removing all dirt, mildew, wax, grease, resin oils, tannins and dust. If Timber is extremely oily or tannin rich, dampen a mop or clean rag with Urethane Coatings THINNERS or MINERAL TURPENTINE and complete a 'Chemical wash' wiping parallel to the grain in a similar manner to applying a coating (NOT in a circular polishing manner). If a large area is to be cleaned, thoroughly rinse the mop or rag every 3 to 5m², re-dampen and continue.
3. Nail holes and surface defects should be filled with water based putty. **[Refer Important Notice # 5 (Pg 3)]**

New Floors: Follow steps 1 to 3 above, sand the floor and fine sand, finishing with 120 grit screen back or pad and vacuum thoroughly.

Old Floors: Follow steps 2 to 3 above and clean with hot water and detergent. Roughen surface completely with 100 grit sandpaper and fine sand, finishing with 120 grit screen back or pad and vacuum thoroughly. Wipe floor with Urethane Coatings THINNERS. Test for compatibility by applying MODIFIED OIL MATT on a small section of floor first. If 'craters' or 'fisheyes' appear add 10mls of Urethane Coatings FLOWMAX Anti Rejection Fluid per Litre of MODIFIED OIL MATT and stir thoroughly. Soon after application, inspect for rejections, and if necessary continue adding FLOWMAX in increments of 10mls per Litre until the surface is free from rejections or up to a maximum of 30mls per Litre of MODIFIED OIL MATT. The addition of FLOWMAX *may* stimulate bubbling or foaming if MODIFIED OIL MATT is excessively agitated and therefore roller rotation speed and vigorous mixing should be minimized during application.

Application Orientation: For interior flooring, including all species of timber, parquetry and particle board.

Application Conditions: Do not use MODIFIED OIL MATT at temperatures below 10°C or above 30°C. On cold days for at least one hour prior to application warm MODIFIED OIL MATT, by wrapping container in an electric blanket (temp setting 1) for up to 2 hours.

Do not use MODIFIED OIL MATT if relative humidity is in excess of 85% AND/OR if the moisture content of timber is in excess of the Australian Standard (9 to 14%).

SHAKE WELL and STIR thoroughly before and during use as MODIFIED OIL MATT contains a silica based matting paste which may settle during the shelf life of this product. [Unstirred MODIFIED OIL MATT will dry glossier than stirred MODIFIED OIL MATT].

Application Method: Apply with short nap (6mm) Mohair or Micro-fibre roller, brush or lamb's wool applicator. Do not return unused material to the can/drum. Touch dry; 1 hour at 25°C and 50% relative humidity, however allow 5.5 to 6.0 hours to fully dry. **Reduced** temperature and/or **increased** humidity **will** slow drying (extend time required to dry). When applying TUNGSEAL and/or MODIFIED OIL allow 8 to 12 hours between 1st and 2nd & 2nd and 3rd coats. Suitable for light foot traffic 24 hours after final coat.

N.B. If the coating does not sand to a fine white powder, leave for a further 24 hours between coats and in extreme cases longer – if possible & practicable operate artificial heating ([Radiator style] Column oil filled electric heaters are preferable - DO NOT operate heating equipment that utilise naked flames or red hot surfaces). Some timber species exude oils and antioxidants which severely retard curing. The curing process is called 'autoxidation' and relies on absorbing oxygen from the atmosphere; both antioxidants and the natural oils in timber inhibit curing.

New Floors: Apply three coats as per all options below.

Old Floors: Apply two coats; 1st as per **SECOND COAT** options (a), (b) or (c) below, then 2nd as per **THIRD COAT and/or Final Coat** below.

FIRST COAT - can be either (a) or (b) or (c) or (d);

- (a) TIMBERSEAL – apply with a Mohair or Micro-fibre roller. Allow 40 to 60 minutes drying, no sanding is required prior to application of second coat.
- (b) DUOTHANE FAST A/DUOTHANE Part B - apply with a Mohair or Micro-fibre roller or lamb's wool applicator. Allow 90 to 120 minutes to dry. Lightly sand with 150 mesh screen-back. Vacuum thoroughly.
- (c) TUNGSEAL – apply with a Mohair or Micro-fibre roller or lamb's wool applicator. Allow overnight to dry. Lightly sand with 150 mesh screen-back, and vacuum thoroughly before the next coat.
- (d) MODIFIED OIL SATIN/GLOSS - apply as per (c) TUNGSEAL above.

N.B. MODIFIED OIL & TUNGSEAL CATALYST may be added to the first and second coats of TUNGSEAL or MODIFIED OIL GLOSS/SATIN to accelerate curing.

SECOND COAT – Apply either (a), (b), or (c);

- (a) DUOTHANE FAST A/DUOTHANE Part B - apply with a Mohair or Micro-fibre roller or lamb's wool applicator. Allow 90 to 120 minutes to dry. Lightly sand with 150 mesh screen-back. Vacuum thoroughly.
- (b) TUNGSEAL – apply with a Mohair or Micro-fibre roller or lamb's wool applicator. Allow overnight to dry. Lightly sand with 150 mesh screen-back, and vacuum thoroughly before the next coat.
- (c) MODIFIED OIL SATIN/GLOSS - apply as per TUNGSEAL (b).

THIRD COAT and/or Final Coat – Apply a very even coat of MODIFIED OIL MATT with a Mohair or Micro-fibre roller or lamb's wool applicator. Application of a consistent film thickness is critical to prevent stop and/or lap marks appearing as MODIFIED OIL MATT dries.

Important Notice: Although MODIFIED OIL MATT is not as subject to sheen variation as low sheen polyurethanes, the 'gloss' (*sheen*) level may increase in conditions of faster drying. Hence open areas such as entrances, may tend to be 'glossier' (*less matt*) than areas with little or no airflow. Accordingly Urethane Coatings recommend;

1. Restrict air flow by sealing under and around doorways, windows, skirting boards, air conditioning ducts/central heating vents, chimneys, cooling fans of refrigerator motors, etc. In extreme cases (to restrict air flow and/or to control airborne dust) it may be necessary to seal over ceiling penetrations such as down lights, lighting roses and air circulation vents.
2. Maintain a wet edge at all times, otherwise a lap mark may appear after curing. As appropriate add 40-60mls of MINERAL TURPENTINE per Litre of MODIFIED OIL MATT.
3. Upstairs floors will tend to be 'glossier' (*less matt*) than downstairs as solvent vapours are heavier than air and will flow to lower levels and thus retard the drying process.
4. Some timber species, notably Brushbox, Blackbutt, and Cypress Pine secrete oils and waxes which may migrate to the surface of the coatings causing surface imperfections. The addition of FLOWMAX Anti Rejection Fluid may assist to alleviate this problem.
5. DO NOT apply reduced sheen products (MODIFIED OIL SATIN, and MODIFIED OIL MATT) directly over putty as the silica in the putty **may** react with the matting agent in MODIFIED OIL turning the putty white – ensure that at least one coat of MODIFIED OIL GLOSS separates putty from reduced sheen coats. (With the exception of putty, it is compatible to apply a MODIFIED OIL reduced sheen product directly over another MODIFIED OIL reduced sheen product [e.g. Apply a coat of MODIFIED OIL MATT directly on-top of MODIFIED OIL MATT]).

Maintenance:

MODIFIED OIL MATT requires 7 to 10 days to fully cure. Avoid heavy foot traffic during this period. After the curing period, regularly sweep with a soft bristle broom or an antistatic mop and as appropriate wash with a mixture of '3 litres of hot water to one cup of Methylated Spirit'. MODIFIED OIL has wearing properties at least equivalent to all other oil based floor coatings. To look after the floor use mats - place a door mat outside each entrance and if possible a softer mat immediately inside each door – this will assist to remove any sand, grit and small stones from shoe-soles/feet, that when walked over the floor are abrasive, acting like sandpaper. We caution against the use of vacuum cleaners, particularly if the bristles are worn as the cleaning head may then scratch the floor. The frequency of cleaning is dependent on the level of traffic, amount of grit carried onto the floor, and activity of children, and pets etc. In high traffic situations a sacrificial wear surface, i.e. a polish is required to take the brunt of the traffic. Suitable polishes are; Urethane Coatings **PURASHINE**, Johnsons One Go, Reckitts Long Life, or Peerless Gemini.

These polishes are water based and easily applied with a foam applicator. Allow at least 10 days for the MODIFIED OIL to cure before application of Polish. USE protective pads under legs of furniture and always avoid dragging furniture over the floor.

Coverage: 10m² per Litre.

Thinning: Thinning is not recommended, however Urethane Coatings MINERAL TURPENTINE or WHITE SPIRIT may be added if MODIFIED OIL MATT has thickened, or if a higher coverage and a thinner coat is required.

Clean Up: Thoroughly wash all equipment with Urethane Coatings CLEANING SOLVENT or MINERAL TURPENTINE. Dry roller, brush, and applicator before reusing.

Packaging: MODIFIED OIL MATT is supplied in 4, and 10 Litre Drums.

Shelf Life: MODIFIED OIL MATT is best if used within 12 months from manufacture, when stored in unopened containers under normal conditions of temperature and humidity. **N.B.** After the drum seal is 'broken' MODIFIED OIL is prone to 'skinning', therefore when decanting a partly used drum strain the MODIFIED OIL through a stocking or stainless steel sieve.

Health & Safety Directions:

For detailed Health and Safety information refer to the MODIFIED OIL Safety Data Sheet (SDS) or visit; www.urethanecoatings.com.au

Use this material in well ventilated conditions. Prevent skin contact by wearing impervious gloves. Avoid breathing of vapour as it may cause lung irritation. May irritate skin and eyes. Keep containers firmly closed when not in use. In case of spillage absorb into dry sand or dirt then remove from work area and complete disposal in responsible manner.

Flammable: MODIFIED OIL MATT contains volatile and flammable solvents and when applying the contents adequate ventilation to the outside must be provided. All potential sources of ignition (open flames, pilot lights, furnaces, spark producing electrical switches, etc.) must be eliminated in or near the working area. DO NOT SMOKE. Keep Drum closed when not in use.

FIRST AID:

Eye Contact: Irrigate affected eye(s) with copious quantities of water for 15 minutes ensuring eyelids are held open. Seek medical advice if any pain or redness develops or persists.

Skin Contact: Wash skin thoroughly with soap and water as soon as possible. Remove contaminated clothing and wash underlying skin. Launder clothing before re-use.

Inhalation: Inhalation of mists, fumes or vapour may irritate the nose or throat. Remove from area of exposure to fresh air, taking care to use respiratory protection so as not to expose self to hazard. If effects persist obtain medical assistance.

Ingestion: Rinse mouth with water. If swallowed, do NOT induce vomiting. Give glass of water. Seek immediate medical advice and/or call poisons information centre, (Australia: 13 1126).

Precautionary Statement: First Aid is generally not required, treat symptomatically. If medical advice is needed, have product container or label at hand. Keep out of the reach of children. Read label before use.

Warranty:

Written claims to be made to seller within 7 days of goods received. Urethane Coatings (UC) warrants its' products to be free of defects in materials, and within their manufacturing specification but makes no warranty as to application and installation. As methods of application and on site conditions are beyond the manufacturers' control and can affect performance, UC makes no other warranty, expressed or implied, including warranties of merchantability and fitness for a particular purpose. Urethane Coatings' sole obligation shall be, at its option, to replace, or refund the purchase of the quantity of Coatings proved to be defective and UC shall not be liable for any loss or damage including incidental or consequential damages arising from the use of UC products.

PRODUCT IDENTIFICATION:

UN No.:	1263	D.G. Class:	3	CAS No.:	PROPRIETARY
HAZCHEM:	3[Y]	PACK. GRP.:	III		
Correct Shipping Name:	Paint.	Manufacturers MANCODE:			URECOAT

Notice to Readers:

Urethane Coatings make no representation as to the completeness and accuracy of the data contained in this Technical Data Sheet. It is the user's obligation to evaluate and use this data, and to comply with all relevant Commonwealth, State and Local Government laws and regulations. Urethane Coatings shall not be responsible for loss, damage or injury resulting from reliance upon or failure to adhere to any recommendations contained herein, from abnormal use of the material, or from any hazard inherent in the nature of the material.

End of Technical Data Sheet